


Divoroll

STANDARD


The economical choice for your everyday membrane suitable for use with tiles, slates or profiled metal roofs on both warm and cold roofs.




KEY ADVANTAGES



Represents value for money whilst still retaining a high level of performance.



A vapour permeable membrane allows moisture to escape giving good ventilation and helping the building breath.



Membrane weight.

PRODUCT CODE	WIDTH	LENGTH	TAPE	COLOUR	LAYERS	ROLL WEIGHT	PALLET QTY
540661	1.5 m	50 m	-	Light grey	3	9.5 kg	20 Rolls

TECHNICAL INFORMATION	Value	Unit	Tolerance [+/-]	Test Method
Colour	Light grey			
Layers	3			
Weight	120	g/m ²	- / + 10%	EN1849-2
Length	50	m	-0%	EN 1848-2
Width	1.5	m	-0.5%/1.5%	EN 1848-2
Straightness	< 30	mm per 10m		EN 1848-2
Tensile Strength (MD)	200	N/50mm	-/+30	EN 12311-1
Tensile Strength (CD)	160	N/50mm	-/+30	EN 12311-1
Elongation MD	30	%	-/+15	EN 12311-1
Elongation (CD)	80	%	-/+15	EN 12311-1
Nail tear resistance (MD)	130	N	-/+30	EN 12310-1
Nail tear resistance (CD)	140	N	-/+30	EN 12310-1
Dimensional stability	2	%		EN 1107-2
Cold flexibility (Pliability)	-20	°C		EN 1109
Sd value	0.03	m	-/+0.01	EN 12572 Method C
Water tightness	W1	Class		EN 1928:2000
Fire Classification	E	Class		EN 13501-1
Water Column	>3000	mm		EN 20811
AGEING PERFORMANCE				EN17872
Water Tightness	W1	Class		EN1928:2000
Tensile strength (MD)	180	N/50mm	-/+30	EN 12311-1
Tensile strength (CD)	130	N/50mm	-/+30	EN 12311-1
Elongation (MD)	17	%	-/+15	EN 12311-1
Elongation (CD)	30	%	-/+15	EN 12311-1
Resistance to air penetration	>0.1	m ³ /(hxm ² x50Pa)		EN 12114
Resistance to temperature	-40/+80	°C		
Exposed maximum UV stability	4	months		EN13859-1:2010
Maximum exposure time	2	weeks		

Product, technical standards and codes of practice are under constant review. We reserve the right to change and amend products and information without prior notice. For the latest information and further advice, please contact your nearest Technical Service team or Customer Services Team. Further information can also be found on our website.

SUSTAINABILITY INFORMATION	
Manufacturer Statement	REACH: Divoroll Standard does not contain any substances that meet the REACH criteria for substances of very high concern. Plasticizer: Divoroll Standard is free of plasticizer Divoroll Standard is free of PFAS
Recycling and Disposal	Divoroll Standard can be disposed of as plastic as it does not require any special handling or disposal procedures.
EU waste codes	Transport packaging shrink film: 150102 Product packaging cardboard & cardboard core: 150101 Interzero Number: 248961 Waste Code Number: 170904


TECHNICAL SUPPORT

<Insert contact details for further information and local Technical Support>

<Telephone> <Email> <Website>



interzero®



Store in dry location away from wind, rain, sun and heat

ADDITIONAL PRODUCTS

(sold separately)



Clima Tape



Divo Tape



Unoroll



Flexiroll Alu



Divoroll Anschlusskleber